

APP Klarlack UHS 410/APP Klarlack UHS 410 Harter

Two-component low-emission, quick drying acrylic Premium class clear lacquer. It features with high content of solids up to 59% and VOC below 410 g/L. It offers very good levelling properties, easy application and polishing. It ensures high gloss and base coat colour fastness.



QUICK APPLICATION- VERY SHORT DRYING TIME

Shortens significantly paint booth operation time:

Ready for assembly at temp.	
+20 °C	– 2,5 h.
+60 °C	– 15 min
IR radiator	– 10-15 min



Application without thinner !

Does not require an elasticizing additive during application on plastic.

High gloss.

Easy polishing.



APP UHS 410 clear lacquer features with resistance to weather conditions in different climatic zones.

Specially designed resins provide lacquer resistance to stone related chipping and other fine damages.



Compatible with both Quick and Standard hardener depending on ambient temperature and area of application.



1 Mixing ratio by volume



2:1 APP Klarlack UHS 410
with hardener
APP Klarlack UHS Harter

2 Coats qty




2x1 (50-60 µm)

3 Application with spray gun




Ø 1,2-1,4

4 Evaporation time between coats



5-10 Min

5 Pressure



2,0-2,5 Bar

ADVANTAGES

+
EASY
APPLICATION

+
APPLICATION
WITHOUT
HARDENER

+
HIGH
GLOSS

+
SMOOTH APPLICATION
ON PLASTIC ELEMENTS
without an elasticizing
additive.

+
HIGH STRENGTH
Resistant to stone
related chipping and other
fine damage.

+
MATERIAL SAVINGS
15-20% comparing
to standard lacquers

**CONTENT OF SOLIDS UP TO 59%.
VOC 420 g/L**

APP No.	Product Description		Volume	Type	Bulk package
020135	APP Klarlack UHS 410	UHS Two-component clear acrylic lacquer	1L	Clear	6 items
020136			5L		3 items
020335	APP Harter Klarlack UHS 410	Acrylic lacquer hardener	0,5l	Standard	6 items
020336			2,5L		3 items
020337	APP Harter Klarlack UHS 410	Acrylic lacquer hardener	0,5l	Quick	6 items
020338			2,5L		3 items

APP Sp. z o.o.

ul. Przemysłowa 10, 62-300 Września

Customer Service Department: Phone. +48 61 437 00 20, bok@app.com.pl

www.APP.com.pl

11.09.2020

